

試驗報告



報告編號：HB-18-09728

C-18-37486

頁數：1 OF 1

報告日期：107年12月18日


委託單位：特欣國際股份有限公司
 供料廠商：特欣國際股份有限公司
 樣品名稱：特麗欣地坪打底乾混砂漿 MD150(DS)
 送驗人員：特欣國際股份有限公司(魏稜芳)
 收件日期：107年12月06日
 試驗日期：107年12月12日~107年12月14日
 備註：1. 以上資料由顧客提供(收件及試驗日期除外)
 2. 除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗方法	試驗結果	CNS 15517(2011) 規範要求值(DS)
稠度(mm)	參考 CNS 15518(2011)	51	45mm~55mm
凝結時間(h) ^(註2)		4.6	3~8
保水性(%)		99.9	≥88
水溶性氯離子含量(kg/m ³)	參考 CNS 13465(2014) 附錄簡易測定法	0.043	0.3

- 註：1. 配比(重量比)= 特麗欣地坪打底乾混砂漿 MD150(DS)：水=100：15.5
 2. 凝結時間配比(重量比)=特麗欣地坪打底乾混砂漿 MD150(DS)：水=100：20.5 (稠度=96mm)
 3. 拌合方式：依照 CNS 3655(1973)拌合壘料之步驟
 4. 水溶性氯離子試驗單位用水量 327 kg/m³

規範要求值僅供參考，合格之判定以委託單位實際要求為準。


 報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.