

試驗報告



報告編號: HM-25-04515

C-25-11671

頁數: 1 OF 1

報告發行日期: 114年 04月 21日

委託品名: 特欣國際股份有限公司
 送驗人: 特麗欣 地坪打底乾混砂漿 MD150
 會收人: 特欣國際股份有限公司(陳玟撰04151640)
 試件: NA
 試驗日期: 114年 04月 15日 17時 00分
 試驗日期: 114年 04月 18日 09時 56分
 試驗方法: CNS 1010:1993

1. 以上資料(送驗人員、會驗人員、試驗方法、試驗數量、收件日期及試驗日期除外)及下述報告內容標示#處係由顧客提供
 2. 除非另有說明,此報告結果僅適用於收取之試驗件
 未經本公司事先書面同意,此報告不可部分複製
 3. 收件方式為實驗室收件;收件地點:新北市五股區(新北產業園區)五權路55號
 4. 本實驗室為公共工程材料實驗室認證服務計畫認可實驗室

試驗結果

試體編號	試體長度	試體寬度	實際量面積	最大荷重		抗壓強度	
	mm	mm	mm ²	kgf	tf	kgf/cm ²	psi
001	51.08	50.15	2561.66	5707	5.71	222.8	3170
002	50.52	50.63	2557.83	5599	5.60	218.9	3110
003	50.75	50.29	2552.22	5272	5.27	206.6	2940

註:#1. 製作日期: 114年 03月 21日

齡期: 28天

#2. 試體之製作由廠商執行

#3. 養護條件: a. 試體拆模後由廠商於室溫下水中養護

b. 試體送至實驗室後以23±1.7°C之飽和石灰水中養護

#4. 設計強度: NA

5. 樣品描述: 水泥壩料立方體試體

6. 本試驗報告之試驗地點於新北市五股區(新北產業園區)五權路55號。

----- o o o -----

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準。

黃玲瓏

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.